

SABIC® PP QR675K

PP random copolymer QRYSTAL for Injection moulding

Description:

SABIC® PP QR675K is a highly transparent random copolymer with good antistatic properties with excellent flow behaviour. This grade combines improved aesthetics of the finished articles with low temperature processability. Part aesthetics are not affected by the lower temperatures, providing for a broader operating window. The SABIC® PP QR675K results in excellent demoulding characteristics and has a good stiffness to impact ratio.

Application: SABIC® PP QR675K is mainly used in injection moulding processes. The SABIC® PP QR675K aims at transparent applications where higher MFI's with good flow are required. Its intended applications include injection moulded housewares, office & home storage boxes, thin wall packaging and media packaging.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>


The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

Typical values

Revision 20100603

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	60	ISO 1133
Density	kg/m ³	905	ISO 1183
Mechanical properties			
Tensile test			ISO 527
stress at yield	MPa	30	
stress at break	MPa	33	
strain at break	%	>50	
Flexural test			ASTM D 790
Flexural modulus	MPa	1200	
Izod impact notched			ISO 180/4A
at 23 °C	kJ/m ²	4.7	
at 0 °C	kJ/m ²	2.5	
Charpy impact notched			ISO 179
at 23 °C	kJ/m ²	3.5	
Optical properties			
Haze	¹⁾ %	7.5	ASTM D 1003

1) Thickness of test specimen: 1mm



SABIC® PP QR675K

PP random copolymer QRYSTAL for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.