

Topilene® HB240P Polypropylene Block Copolymer

For PP-B Pipes and Fittings(Non-Pressure Pipes)

Product Description

Topilene® HB240P is a specially designed polypropylene block copolymer (PP-B, natural colored) that features excellent long-term hydrostatic pressure resistance. It is suitable for underground drainage & sewage pipes and fittings. It is the outcome of HYOSUNG's integrated polymerization and crystallization technology with advanced PP manufacturing process technique.

Characteristics

| | |
|----------------------------|---|
| Typical Application | Drainage & sewage pipes and fittings (Solid wall & twin wall corrugated pipes system) / Industrial pipes |
| Features | Excellent long-term hydrostatic pressure resistance / Excellent stiffness and impact strength balance / Enhanced big diameter pipe manufacturing processability / Chemical stability / Environment-friendly |
| Compliance | The pipes produced with Topilene® HB240P complies with the hydrostatic pressure requirements according to ISO/DIS 15874. It complies with the requirements of FDA 21 CFR 177.1520. This product corresponds to GB/T17219-1998 for drinking water system. |

Typical Properties

| Resin Properties | Method | Value | Unit |
|--|------------|------------------|----------|
| Melt Index(230°C, 2.16kg) | ASTM D1238 | 0.30 | g/10min |
| Density | ASTM D792 | 0.90 | g/cm³ |
| Tensile Strength at Yield | ASTM D638 | 320 | kg/cm² |
| Flexural Modulus | ASTM D790 | 15,000 | kg/cm² |
| Notched Izod Impact Strength(23°C / -10°C) | ASTM D256 | N.B / 5.0 | kg-cm/cm |
| Rockwell Hardness | ASTM D785 | 85 | R-Scale |
| Heat Deflection Temperature | ASTM D648 | 120 | °C |
| Vicat Softening Point | ASTM D1525 | 155 | °C |

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

Contacts

| | |
|--------------------|--|
| Head Office | 235, Banpo-daero, Seocho-gu, Seoul, Korea 06578 Tel: +82-2-2146-5451~7 Fax: +82-2-2146-5428 |
| Online | www.hyosung.com www.topilene.com |



Topilene® HB240P Polypropylene Block Copolymer

For PP-B Pipes and Fittings(Non-Pressure Pipes)

Process Guidelines

The actual extrusion conditions will depend on the type of equipment and the SDR of pipes produced. The below conditions may be used as guidelines for this material.

| | |
|-----------------------|-----------|
| Cylinder feeding zone | 170-190°C |
| Cylinder melting zone | 190-225°C |
| Cylinder mixing zone | 200-235°C |
| Head | 200-235°C |
| Die | 200-235°C |
| Melt temperature | 200-235°C |
| Cooling temperature | 20-30°C |

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG CORPORATION. *Topilene®* is a registered trademark owned or used by HYOSUNG CORPORATION.

Contacts

Head Office 235, Banpo-daero, Seocho-gu, Seoul, Korea 06578
 Tel: +82-2-2146-5451~7 Fax: +82-2-2146-5428

Online www.hyosung.com
www.topilene.com

