



# SABIC® PP 83EK10

## PP block copolymer for Sheet extrusion

### Description:

This grade has low flow properties and a very high impact resistance, even at low temperatures. This grade has furthermore an exceptional high stiffness. It is used for flat sheets, corrugated board and flexible pipe.

### Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

### Typical values

Revision 20050719

Properties	Unit (Si)	Values	Test methods
<b>Polymer properties</b>			
<b>Melt flow rate (MFR)</b> at 230 °C and 2.16 kg at 230 °C and 5 kg	g/10 min g/10 min	<b>1.2</b> -	ISO 1133
<b>Density</b>	kg/m <sup>3</sup>	<b>905</b>	ISO 1183
<b>Mechanical properties</b>			
<b>Tensile test</b> stress at yield stress at break strain at break	MPa MPa %	<b>28</b> <b>38</b> <b>&gt;500</b>	ISO 527
<b>Flexural test</b> Flexural modulus	MPa	<b>1300</b>	ASTM D 790
<b>Izod impact notched</b> at 23 °C at 0 °C at -20 °C	kJ/m <sup>2</sup> kJ/m <sup>2</sup> kJ/m <sup>2</sup>	<b>No Break</b> <b>25</b> <b>9.0</b>	ISO 180/4A
<b>Charpy impact notched</b> at 23 °C at 0 °C at -20 °C	kJ/m <sup>2</sup> kJ/m <sup>2</sup> kJ/m <sup>2</sup>	<b>40</b> <b>25</b> <b>8.0</b>	ISO 179
<b>Hardness Shore D</b>	-	<b>68</b>	ISO 868
<b>Thermal properties</b>			
<b>Heat deflection temperature</b> at 1.80 MPa (HDT/A) at 0.45 MPa (HDT/B)	°C °C	<b>50</b> <b>85</b>	ISO 75/A ISO 75/B
<b>Vicat softening temperature</b> at 10 N (VST/A) at 50 N (VST/B)	°C °C	<b>147</b> <b>68</b>	ISO 306/A ISO 306/B

All information supplied by or on behalf of any of the SABIC Europe companies in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but the relevant SABIC Europe company assumes no liability whatsoever in respect of application, processing or use made of the afore-mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore-mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to any of the SABIC Europe companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the afore-mentioned information or products by the user.