



SABIC® PP PHC27

PP block copolymer for Injection moulding

Description:

This grade combines very high impact resistance, also at low temperatures, with a good stiffness and offers very good flow properties. Due to its narrow molecular weight distribution and very low tendency to warp, it is highly suitable for injection moulding of crates, boxes, suitcase shells and automotive parts.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

Typical values

| Properties | Unit (Si) | Values | Test methods |
|--|---|---|------------------------|
| Polymer properties | | | |
| Melt flow rate (MFR) at 230 °C and 2.16 kg at 230 °C and 5 kg | g/10 min g/10 min | 14 60 | ISO 1133 |
| Density | kg/m ³ | 905 | ISO 1183 |
| Mechanical properties | | | |
| Tensile test stress at yield stress at break strain at break | MPa MPa % | 22 19 600 | ISO 527 |
| Flexural test Flexural modulus | MPa | 1200 | ASTM D 790 |
| Izod impact notched at 23 °C at 0 °C at -20 °C | kJ/m ² kJ/m ² kJ/m ² | No Break 9.0 6.0 | ISO 180/4A |
| Charpy impact notched at 23 °C at 0 °C at -20 °C | kJ/m ² kJ/m ² kJ/m ² | 31 12.5 7.0 | ISO 179 |
| Hardness Shore D | - | 66 | ISO 868 |
| Thermal properties | | | |
| Heat deflection temperature at 1.80 MPa (HDT/A) at 0.45 MPa (HDT/B) | °C °C | 52 87 | ISO 75/A ISO 75/B |
| Vicat softening temperature at 10 N (VST/A) at 50 N (VST/B) | °C °C | 140 57 | ISO 306/A ISO 306/B |

All information supplied by or on behalf of any of the SABIC EuroPetrochemicals companies in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but the relevant SABIC EuroPetrochemicals company assumes no liability whatsoever in respect of application, processing or use made of the afore-mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore-mentioned information or product, whose quality and other properties he shall verify, or any property by reason of the application, processing or use of the afore-mentioned information or products by the user.
SABIC Polypropylenes B.V. Trade Register Zuid Limburg nr 14030315.