

## Provisional Product Data Sheet

### SUMITOMO POLYPROPYLENE

## **AR764**

Block Copolymer, Injection

Applications	For general purpose applications such as crates, pails and containers, thin walled packaging, electrical appliances, housewares, etc.
Characteristics	High flow, high impact, high stiffness and high heat stability, with nucleating and antistatic agent.
Typical Processing Conditions	Temperature            190 – 230°C Mould Temperature    30°C

### Typical Properties

Physical		Value	Unit	Method
Melt Flow Rate	2.16kg	25	g/10min	ISO 1133
Density		0.900	g/cm <sup>3</sup>	ISO 1183
Mechanical		Value	Unit	Method
Tensile Strength	at Yield	26	MPa	ISO 527-1,2
	at Break	16	MPa	ISO 527-1,2
Tensile Elongation	at Break	100	%	ISO 527-1,2
Tensile Modulus		1420	MPa	ISO 527-1,2
Charpy Impact, Notched	23°C	8	kJ/m <sup>2</sup>	ISO 179
	-20°C	4	kJ/m <sup>2</sup>	ISO 179
Rockwell Hardness		89		ISO 2039-2
Thermal		Value	Unit	Method
Vicat Softening Temperature	50N	72	°C	ISO 306B
Other		Value	Unit	Method
Flammability		HB		UL 94

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications. Actual test results may vary.  
Test pieces preparation condition as per ISO 1873-2.

**Manufacturer**

AR764 is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh).

**Food Contact Application**

Unmodified AR764 complies with the EU Directive 2002/72/EC and its amendments 2004/1/EC, 2004/19/EC, 2005/79/EC, and 2007/19/EC for use in direct contact with food. Please contact your nearest SCA representative for more detailed information.

**Restriction of Hazardous Substances**

The substances regulated under EU Directive 2002/95/EC on RoHS in electrical and electronic equipment are not used in the manufacturing process of AR764 and are therefore not expected to be present.

**Storage and Handling**

AR764 is supplied in 25kg bags or in bulk containers depending on packaging options available for different markets. It is advisable to store in a well ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odor characteristic of the resin.

Please refer to the Material Safety Data Sheet (MSDS) for information regarding industrial health and safety issues.

**Disposal and the Environment**

SCA prioritizes environmental management in all our operations in responsibility and respect towards the community and the world around us.

Unmodified, our polypropylene and polyethylene products are readily recyclable, both for reuse via reprocessing, and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

**Office Locations****SUMITOMO CHEMICAL EUROPE S.A./N.V.**

Woluwelaan, 57, B-1830 Machelen BELGIUM

Phone +32 2 2548799

Fax +32 2 2512991

Web Site [www.sumitomo-chem.be](http://www.sumitomo-chem.be)

**SUMITOMO CHEMICAL EUROPE N.V.**

Turkey Liaison Office, Fatih Sultan Mehmet Cad. Yayabeyi Sok. Ilayda Is Mrk, No.12/2, 34810 Kavacik, Beykoz - Istanbul - TURKEY

Phone +90 216 680 3334

Fax: +90 216 680 1012

**SUMITOMO CHEMICAL ASIA PTE LTD**

150 Beach Road #18-05/08 Gateway West SINGAPORE 189720

Phone +65 63035188

Fax +65 62989621

Web Site [www.sca.com.sg](http://www.sca.com.sg)

**SUMITOMO CHEMICAL ASIA PTE LTD**

Vietnam Representative Office, 7th Floor, Unit 701-3, Me Linh Point Tower, 2 Ngo Duc Ke Street, Dist. 01, Ho Chi Minh City VIETNAM

Phone +84 8 5202767

Fax +84 8 5202911

**SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.**

Unit 46-07 Grand Gateway II, No.3 Hongqiao Road, Xu Hui District, Shanghai CHINA 200030

Phone +86 21 64482255

Fax +86 21 64077365

**SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.**

Unit 12E-2 Block C Peace Square, Shenghe Road, Nancheng District, Dongguan, Guangdong CHINA 523071

Phone +86 769 22887316

Fax +86 769 22887885

**SCA SOUTH ASIA PETROCHEMICALS PRIVATE LIMITED**

Sethi Chambers, Plot No.2, D.D.A. Local Shopping Centre, 2nd Floor, M.O.R. Land, New Rajinder Nagar, New Delhi – INDIA 110060

Phone +91 11 2874 1571

Fax: +91 11 2874 1565

**Disclaimer**

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications. All information contained in this document is provided in good faith and believed to be reliable on the date compiled. Customer is responsible to ensure that SCA materials, whether used alone or in conjunction with other materials, are suitable for the intended application. SCA accepts no liability whatsoever for any action taken based on this information, and/or for any loss and consequential loss or damage. Please contact your nearest SCA representative for more detailed information.